





VLASPLATEN
 FLACHSPANPLATTEN
 PANNEAUX DE LIN
 FLAXBOARDS

LINOPAN N.V.
 OOIGEMSTRAAT 16 (ZONE IV)
 B-8710 WIELSBEKE
 BELGIUM

HOUTSPAANPLATEN
 HOLZSPANPLATTEN
 PANNEAUX DE BOIS
 CHIPBOARD

TEL: +32-56-667383
 FAX: +32-56-665255
 E-MAIL: info@linopan.be

PROPERTIES		29/03/2004	flaxboard D 450	
UNIT				
Density tolerance	EN 323	Kg/m ³		± 8 %
Thickness tolerance between panels within panel	EN 324.1	mm		± 0,3
		mm		0,2
Bending strength	EN 310	N/mm ²		8
Modulus of elasticity	EN 310	N/mm ²		1350
Tensile strength	EN 319	N/mm ²		0,2
Surface strength	EN 311	N/mm ²		0,65
Screw holding	EN 320			
		N		550
		N		400
Moisture content	EN 322	%		5 up to 10
Dimensions	EN 324-1			
Width		mm		± 1
Length		mm		± 1
Squareness	EN 324-2	mm/m		± 1
Sand content	ISO 3340	%		< 1
Formaldehyd emission (perforator)	EN 120	mg HCHO/100gr		< 8