



VLASPLATEN FLACHSSPANPLATTEN (ZONE IV) PANNEAUX DE LIN FLAXBOARDS	LINOPAN N.V. OOIGEMSTRAAT 16 B-8710 WIELSBEKE BELGIUM
HOUTSPAANPLATEN HOLZSPANPLATTEN PANNEAUX DE BOIS MAIL: info@linopan.be	TEL: +32-56-667383 FAX: +32-56-665255 E-

PROPERTIES		8/10/2004	Filling and packing material				
		UNIT	Type A	Type B	Type C	Type D	Type E
Density tolerance	EN 323	Kg/m ³	± 8 %	± 8 %	± 8 %	± 8 %	± 8 %
Thickness tolerance between panels	EN 324.1	mm	± 0,3	± 0,3	± 0,3	± 0,3	± 0,3
within panel		mm	0,2	0,2	0,2	0,2	0,2
Bending strength	EN 310	N/mm ²	4,5	5,5	6	7	8
Modulus of elasticity	EN 310	N/mm ²	750	800	900	1100	1350
Tensile strength	EN 319	N/mm ²	0,1	0,1	0,15	0,18	0,2
Thickness swelling 24 hours	EN 317	%	< 18	< 15	< 15	< 15	< 15
Moisture content	EN 322	%	5 up to 10	5 up to 10	5 up to 10	5 up to 10	5 up to 10
Dimensions	EN 324-1	mm	± 1	± 1	± 1	± 1	± 1
Width		mm	± 1	± 1	± 1	± 1	± 1
Length	EN 324-2	mm/m	± 1	± 1	± 1	± 1	± 1
Squareness		mm/m	± 1	± 1	± 1	± 1	± 1
Sand content	ISO 3340	%	< 1	< 1	< 1	< 1	< 1
Formaldehyd emission (perforator)	EN 120	mg HCHO/100gr atro	< 8	< 8	< 8	< 8	< 8