




VLASPLATEN  
 FLACHSPANPLATTEN  
 PANNEAUX DE LIN  
 FLAXBOARDS

LINOPAN N.V.  
 OOIGEMSTRAAT 16 (ZONE IV)  
 B-8710 WIELSBEKE  
 BELGIUM

HOUTSPAANPLATEN  
 HOLZSPANPLATTEN  
 PANNEAUX DE BOIS  
 CHIPBOARD

TEL: +32-56-667383  
 FAX: +32-56-665255  
 E-MAIL: info@linopan.be

PROPERTIES		9/06/2004	mixboard D 550 30% Flax / 70 % Wood	
		UNIT		
Density tolerance	EN 323	Kg/m3	± 8 %	
Thickness tolerance between panels	EN 324.1	mm	± 0,3	
within panel		mm	0,2	
Bending strength	EN 310	N/mm2	9	
Modulus of elasticity	EN 310	N/mm2	1500	
Tensile strength	EN 319	N/mm2	0,2	
Surface strength	EN 311	N/mm2	0,8	
Screw holding 	EN 320	N	650	
		N	450	
Moisture content	EN 322	%	5 up to 10	
Dimensions	EN 324-1	mm	± 1	
Width		mm	± 1	
Length		mm	± 1	
Squareness	EN 324-2	mm/m	± 1	
Sand content	ISO 3340	%	< 1	
Formaldehyd emission (perforator)	EN 120	mg HCHO/100gr	< 8	