




VLASPLATEN
 FLACHSPANPLATTEN
 (ZONE IV)
 PANNEAUX DE LIN
 FLAXBOARDS
 HOUTSPAANPLATEN
 HOLZSPANPLATTEN
 PANNEAUX DE BOIS
 MAIL: info@linopan.be

LINOPAN N.V.
 OOIEMSTRAAT 16
 B-8710 WIELSBEKE
 BELGIUM
 TEL: +32-56-667383
 FAX: +32-56-665255
 E-

PROPERTIES		8/10/2004	Quality work-tops			
			< 25	25-34	35-44	45-60
		UNIT	Type E	Type E	Type E	Type E
Density tolerance	EN 323	Kg/m ³	± 8 %	± 8 %	± 8 %	± 8 %
Thickness tolerance between panels within panel	EN 324.1	mm	± 0,3	± 0,3	± 0,3	± 0,3
		mm	0,2	0,2	0,2	0,2
Bending strength	EN 310	N/mm ²	9	9	8,5	8
Modulus of elasticity	EN 310	N/mm ²	1650	1650	1500	1400
Tensile strength	EN 319	N/mm ²	0,3	0,25	0,25	0,25
Surface strength	EN 311	N/mm ²	1	1	1	0,85
Screw holding 	EN 320	N	600	600	600	600
		N	400	400	400	400
Thickness swelling 24 hours	EN 317	%	< 12	< 12	< 12	< 12
Moisture content	EN 322	%	5 up to 10	5 up to 10	5 up to 10	5 up to 10
Dimensions	EN 324-1					
Width		mm	± 1	± 1	± 1	± 1
Length		mm	± 1	± 1	± 1	± 1
Squareness	EN 324-2	mm/m	± 1	± 1	± 1	± 1
Sand content	ISO 3340	%	< 1	< 1	< 1	< 1
Formaldehyd emission (perforator)	EN 120	mg HCHO/100gr atro	< 8	< 8	< 8	< 8